

Conductive Foam - High Density

Features:

- Carbon impregnated conductive polyurethane foam
- Non corrosive
- Ideal for cushioning product in transit
- Custom sizes cut to order

Antistat can assist and advise on a vast range of cross linked closed cell foams for specialist applications please contact one of our experienced sales team on +44 (0) 1473 836 200.



Property	Test Method	Requirement
Foam Type	N/A	Polyether polyurethane foam impregnated with flexible conductive latex
Density (kg/m ³)	BS 4443 Pt1 Method 2	24 minimum
Tensile Strength (KPa)	BS 4443 Pt1 Method 3A	70 minimum
Elongation @ Break (%)	BS 4443 Pt1 Method 3A	100 minimum
Loss in Tensile Strength After Heat Ageing (%)	BS 4443 Pt1 Method 3A 140oC for 16 hours	30% Max Loss
Loss in Tensile Strength After Humidity Ageing (%)	BS 4443 Pt1 Method 3A 105oC for 3 hours	30% Max Loss
Compression Set (50% Compression)	BS 4443 Pt1 Method 3A	30% Max Loss
Volume Resistivity (ohms/m)	BS 2044 Pt1 Method 3 (100V)	250 maximum
Surface Resistivity (K ohms)	Megger BM201 (100V)	<20
Compression Deflection at 50% Compression	BS 4443 Pt1 Method 5A	3.3 KPa (Typical Value)

Important Notice: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © Antistat 2020.

Conductive Foam - High Density

Product Code	Description	Size (LxWxD) (mm)	Additional Notes
038-0016	High Density Conductive Foam	305 x 305 x 6	Black - Min 100 units
038-0002	High Density Conductive Foam	1000 x 1000 x 6	Black - Min 10 units



Buy online at
www.antistat.com



Call us on
 +44 (0)1473 836 200



Email us at
info@antistat.com



Message us on Live Chat
www.antistat.com

Important Notice: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © Antistat 2020.