

Non-Indicating Silica Gel, Granular

A narrow pored granular form of amorphous silica free from extraneous matter. The irregular granules are a white/translucent colour.

They remain physically unchanged when dry and when saturated with water.



Typical Properties

Moisture content at 145°C 2% maximum Equilibrium capacity for water vapour at 25°C and given relative humidity (r.h.)	2% maximum
10% r.h.	> 6½ % w/w (weight for weight)
20% r.h.	> 12% w/w
50% r.h.	> 27% w/w
80% r.h.	> 36% w/w

BET Surface Area	600 - 800 m ² /g
Pore volume	0.35 - 0.45 ml/g
Average pore diameter	20 - 30 Å
pH (10% aqueous solution)	Not less than 3.5
Bulk density	700 - 770 g/l

Water soluble sulphates	1.0% maximum
Water soluble chlorides	0.05% maximum
Ammonia/ammonium compounds	10mg/kg maximum
Friability and dust	Not more than 0.5% less than 125 micron

Important Notice: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © Antistat 2020.

Non-Indicating Silica Gel, Granular

Particle Sizes	Very Fine	0.2 – 0.5 mm
	Fine	0.5 – 1.0 mm
	Medium	1.0 – 3.0 mm
	Coarse	3.0 – 6.0 mm
Toxicity	Non-toxic	
Storage	Packages should be kept closed and in a dry place	
Shelf life	Shelf-life of between one and three years depending on packing type	
Regeneration can be carried out at temperatures between 120°C and 150°C.		

Packaging design may vary. This material meets the requirements of BS 2540:1991 Granular Desiccant Silica Gel, DIN 55473:2001-2002 and Mil-D-3464E

Product Code:	Nominal Dessicant Content (g)	Nominal Dimensions W x L (mm)	Qty/Box
309-0077	0.5	15mm x 30mm	500
309-0079	1	20mm x 35mm	250
309-0080	3	25mm x 54mm	250
309-0081	10	40 mm x 75mm	100
309-0082	25	50mm x 110mm	100
309-0083	50	78mm x 115mm	100
309-0084	100	93mm x 125mm	100



Buy online at
www.antistat.com



Call us on
 +44 (0)1473 836 200



Email us at
info@antistat.com



Message us on Live Chat
www.antistat.com

Important Notice: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © Antistat 2020.