

PRODUCT

Clay Desiccant In Tyvek



DESCRIPTION

Antistat clay bags exceed the moisture vapour absorption of silica gel preventing corrosion and moisture damage.

FEATURES

- 3 side seal
- Extremely tough, durable sheet of spun bonded polyethylene fibres
- Shelf life: 1 year

PRINT

**CLAY
DESICCANT
1 UNIT
MIL-D-3464E
DIN 55473
DO NOT EAT**

PRODUCT CODE	DESCRIPTION	SIZE (g)	QUANTITY (per bag)
309-0011	Clay Desiccant	25	500 pcs
309-0017	Clay Desiccant	10	100 pcs

Weight and Bag Dimensions

Content Description	Montmorillonite or Bentonite Clay
Bag Material	Tyvek Film

To request a quotation or for more information, please call **+44 (0) 1473 836 200**
email info@antistat.com or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2021 Antistat.

Clay Desiccant Characteristics

Appearance	Granule 1 – 5mm
Colour	Whitish Grey
Bulk Density	700 +/- 50gram per litre
Ph	7.0 +/- 0.5

Moisture Absorption Capacity

Relative Humidity	Grams Of Moisture Absorbed For 25g
20%	Minimum 12%
90%	Minimum 20%

Desiccant Bag Information

Bag Material FH	Material with Printing
Strength Of Bag	Passes Drop Test
Bag Seal Width	Minimum 10mm (±5mm)

Other Information

Storage	Keep desiccant in a dry and sheltered place away from water and sunlight.
Special Instruction	During production, ensure that the lid of the container is closed at all times when not extracting desiccant bags from container.

To request a quotation or for more information, please call **+44 (0) 1473 836 200**
email info@antistat.com or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2021 Antistat.